

Technical Data Sheet

Barton Fosfato de Zinc AQUA

Alkyd anticorrosive primer

Antioxidant protection for any type of metallic surface formed by water base oil synthetic resins, mineral fillers and pigments based antioxidants zinc phosphate.

Typical Uses

- Antioxidant primer for any type of steel surfaces
- Fireproof primer of FIREFILM intumescent paint system.

Surface

Clean, solid, dry and exempt of dust, oils and grease. Remove the existing oxide and all the loose material

Application

Stir the contents of the package. The product can be applied by brush, roller or spray. It is advisable to dilute the paint with a 5% of water to obtain the desired brushability. The recommended thickness for good protection is 40 microns dry film.

Precautions

- Completely remove the remains of loose material.
- Clean utensils are made with water immediately after use.
- BARTON FOSTAFO DE ZINC AQUA should not apply when the substrate temperature is below 5 ° C or above 40 ° C.
- Surface temperature must be above 3 ° C of dew point
- Refer to Product Safety Data Sheet for handling recommendations.

Physical Data

Finish	Matt
Color	Grey, red and white
Substrate	Steel
Dry film	40 µm
Component	1
Volume Solids by weight	54 %
Theoretical coverage	13,5 m ² /l for 40 µm
Drying Time at touch	60 min. at 25° C
Drying Time for recoat	10 hours at 25 ° C
Specific Weight	1,40 g/ml
Application	Airless, brush or roller
Solvent	DP
Solvent Flash Point	31°C
Dilution	
Brush	0-5 %
Roller	0-5 %
Airless	5-10 %
Application Conditions	
Temperature	5 °C a 40 °C
Humidity	0 % a 85 %
Packaging	Paint Can of 18 liters
Weight delivery	30 kg aprox.
Storage	Maximum one year after the delivery date. It should be stored indoors in the original unopened

Technical data sheet edition: January 2019

The information of data sheet is based on our knowledge and experience to date, and is given for information only. It will not be our responsibility anomalies caused by the misuse of the product.